

CLAIMS

1. A fluorine-containing elastomer composition comprising
a fluorine-containing elastomer and a carbon allotrope (except for
5 amorphous carbon) having an average primary particle size of at most
0.1 μm .

2. The fluorine-containing elastomer composition of Claim
1, wherein the carbon allotrope having an average primary particle size
10 of at most 0.1 μm is diamond.

3. The fluorine-containing elastomer composition of Claim
1 or 2, wherein the fluorine-containing elastomer is a
perfluoroelastomer.
15

4. The fluorine-containing elastomer composition for a
semiconductor manufacturing equipment of Claim 1, 2, or 3.

5. A molded article comprising the fluorine-containing
20 elastomer composition of Claim 1, 2, 3 or 4.

6. A sealing material comprising the fluorine-containing
elastomer composition of Claim 1, 2, 3 or 4.

25 7. A filler for a sealing material in a semiconductor
manufacturing equipment comprising a carbon allotrope (except for
amorphous carbon) having an average primary particle size of at most

0.1 μm .